

# Technical Specifications

## SPLENDOR-0.70mm

S.NO.	PROPERTIES	TEST METHOD AS PER BS EN 438 PART 2 & 3: 2016	UNIT	SPECIFIED VALUES	GREENLAM SPLENDOR TYPICAL VALUES
1	Classification	EN 438-3.5.3		HGS	
2	Thickness	EN 438-3 - 6.3	mm	0.7	0.65-0.70
	Thickness Tolerance		mm	± 0.10	± 0.05
3	Resistance to Surface Wear	EN 438-2 - 10	Rev. (min.)	350	400
4	Resistance to Impact with Small Diameter Ball	EN 438-2 - 20	N (min.)	20	25
5	Resistance to Scratching	EN 438-2 - 25	Rating (min.)	3	≥ 3
6	Dimensional Stability at Elevated Temperatures	EN 438-2 - 17			
	Machine Direction		% (max.)	0.55	0.39
	Cross Direction		% (max.)	1.05	0.55
7	Resistance to Immersion in Boiling Water	EN 438-2 - 12	Rating (min.)	For Gloss Finish-3 For Other Finish-4	≥ 3 ≥ 4
8	Resistance to Wet Heat 100°C	EN 438-2 - 18	Rating (min.)	For Gloss Finish-3 For Other Finish-4	≥ 3 ≥ 4
9	Resistance to Dry Heat 160°C	EN 438-2 - 16	Rating (min.)	For Gloss Finish-3 For Other Finish-4	≥ 3 ≥ 4
10	Resistance to Stain	EN 438-2 - 26	Rating (min.)		
	Group 1 & 2			5	5
	Group 3			4	≥ 4
11	Resistance to Steam	EN 438-2 - 14	Rating (min.)	For Gloss Finish-3 For Other Finish-4	≥ 3 ≥ 4
12	Resistance to Color Change in Xenon-Arc Light	EN 438-2 - 27	Rating (min.)	4 to 5	≥ 5
13	Density	EN ISO 1183 -1	g/cm <sup>3</sup> (min.)	1.35	1.40

**Note:** Whereas Greenlam products are manufactured thoroughly to standards, the nature of the application procedure is beyond our control. The values given above are to the best of knowledge but without liability/warranty, expressed or implied.